

Abstract

Metal alloys having low electrical and thermal conductivity including relatively large fractions of P-Group element additions. The P-Group elements may be selected from the group including phosphorous, carbon, boron, and silicon. The resultant alloys
5 do not exhibit significantly increased brittleness, and are applied as a coating that provides a metallic thermal barrier coating.